



Typical Properties of

Noryl® Glass

Modified Polyphenylene Oxide-Styrene with 30% Glass

Process: Extruded

Property	Test Method	Unit	Value
Specific Gravity	D792	--	1.36
Tensile Strength	D638	psi	17,800
Tensile Modulus	D638	psi	N / A
Elongation	D638	%	5
Flexural Strength	D790	psi	20,000
Flexural Modulus	D790	psi	1,100,000
Compressive Strength	D695	psi	11,500
Compressive Modulus	D695	psi	300,000
Hardness, Rockwell	D785	--	R126
Hardness Durometer	--	--	N / A
Izod Impact (notched)	D256	ft. lb of notch	2.3
Coeff. of Friction (Dynamic)	--	dry v.s steel	N / A
Coeff. of Linear Therm. Expan.	E831/ D696	in./in./°F	1.4×10^{-5}
Continuous Use Temperature	--	°F	220
Heat Deflection Temperature	D648	°F	275
Glass Transition Temperature	D3418	°F	140
Melting Point	D3418	°F	310
Thermal Conductivity	E1530-11	BTU in/hr ft ² °F	1.94
Dielectric Strength	D149	Volts/mil	530
Surface Resistivity	EOS/ESD 511.11	ohm/square	$>10^{17}$
Flammability	UL94	--	V-0
Water Absorption, 24 hrs.	D570	% by weight	0.06
Water Absorption, Saturation	D570	% by weight	0.2
Limiting PV (4:1 Safety Factor)	--	--	N / A
K-Factor	--	--	N / A
FDA Compliance	--	--	No

Note: The data provided is for reference purposes only. Additional testing may be required for design specifications or quality control.
All values at 73 F unless otherwise stated.